

Durasyn[®] 180 R

Durasyn 180R high viscosity polyalphaolefin is a fully synthesized and hydrogenated hydrocarbon base fluid produced from C10 linear alphaolefin feed stocks. Its engineered physical and performance properties are designed to extend the service life and enhance the performance of fully formulated lubricants operating under continuous low, high, or wide temperature range conditions.

Features and Benefits

- Inherent thermal stability** ⇒ Resistant to thermal break down under high temperature conditions.
- Inherently resistant to oxidation** ⇒ Allows the formulation of extended drain lubricants
- Engineered to be highly shear stable** ⇒ Maintains viscosity grade over extended service life
- Designed-in broad range viscometrics** ⇒ Suitable for exposure to low or high start-up or operating temperatures, or operation over wide temperature ranges

Intended Applications

Durasyn 180R is engineered for use in a wide variety of applications where the physical and performance properties of fully synthesized PAOs can be beneficial including:

- Gear Oils
- Compressor oils
- Greases
- Industrial Oils

Compatibility

Durasyn 180R has been engineered to be either a near or direct substitute for existing PAO fluids and premium quality oils. Compatibility with metals, elastomers, coatings and sealants is similar to other fully synthesized PAO base fluids. Solubility is also similar to other fully synthesized PAO base oils.

TYPICAL PROPERTIES

Property	Test Method ISO/ASTM or	Unit Value	Unit Range
Specific Gravity , 15.6°C (60°F), kg/l (LB/gal)	12185 / D4052	0.850	0.845 – 0.855
Viscosity Index	2909 / D2270	197	185 min
Viscosity , mm ² /s (cSt), 100°C (212°F)	3104 / D445	98	97.0 – 115.0
Viscosity , cSt, mm ² /s (cSt), 40°C (104°F)	3104 / D445	927.5	900 - 1080
Water , ppm,	D3401	8	50 max

Product Datasheet

TYPICAL PROPERTIES (Continued)

Property	Test Method ISO/ASTM or	Unit Value	Unit Range
Pour Point, °C (°F)	3016 / D97	-40	-20 max
Flash Point COC, °C (°F)	2592 / D92	290	270 min
Flash Point PMC, °C (°F)	2592 / D93	258	-
Noack Volatility, 250°C, 1hr,%wt. Evap.	CEC L-40-A-93	1.2	-
Neutralizing Number (TAN), mg KOH/g	6618 / D974	0.004	<0.1 max
Bromine Number, g Br/100 g	--/ IP-129	0.2	0.4 max
Aniline Point, °C		-	-
Appearance		Clear/Bright	Observation
Color	D1209	<0.5	50 max
% Transmission @ 440 nm		99	>98

Technical information and/or assistance contained herein and/or a sample(s) provided in conjunction with the correspondence, is furnished without charge or obligation, and are given and accepted at the recipient's sole risk. Reasonable efforts were made to verify this information, however, as conditions of use are beyond our control, INEOS makes no representation about, and is not responsible or liable for, the accuracy or reliability of such data, the results obtained therefrom nor toxicological effects of the material(s) described herein. Any sample(s) provided in conjunction with this correspondence is considered to be in the developmental stage, and the characteristics of any subsequent product delivered may vary from the characteristics of the product enclosed. NO WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING BUT NOT LIMITED TO THE WARRANTIES OF MERCHANTABILITY OR FITNESS FOR PARTICULAR PURPOSE, ARE MADE HEREIN OR BY THE PRODUCT PROVIDED. Nothing contained herein shall constitute a permission or recommendation to practice any invention covered by a patent without a license from the owner of the patent.

Review the companion Material Safety Data Sheet (MSDS) for pertinent information regarding the safe use and handling of this product. Information contained in this bulletin is the property of INEOS and may not be redistributed to third parties or posted to a Web site.